


Betoncord® / 10 Concr

Image not found or type unknown



grout and other abrasive and wet medium.

Felirat: ® BETONCORD® CONCRETE / BETON PN 10 BAR

Operating pressure: 10 bar

Bursting pressure: 30 bar

Heat resistance: -30°C / +80°C

Interior: Nr/SBR, black, smooth

Exterior: SBR, black, smooth, fabric imprinted

Linings: fabric linings

Elektromos ellenállás: 106 Ω

Kopás érték: 70 mm³ according to ISO 4649 (earlier DIN 53516) standard

Storage lots, splitting of the rolls are possible. Meantime, we hold the right of selling the stock in products.

Inside Ø (mm)	Wall thickness (mm)	Outside Ø (mm)	Roll size (m)	Article number
60	10	80	20/40	3521 060000
63	13,5	90	40	3521 063090

*Label: BETONHOSE 10 BAR diameter

Inside Ø (mm)	Wall thickness (mm)	Outside Ø (mm)	Roll size (m)	Article number
*50	8	66	40	104500
*60	8	76	40	104501
*63	8	79	40	104502